# TECHNICAL DATA SHEET: TRANSVIR 50 IND

Kraft 100% white cellulose, not trated, with a compact and glazed surface, that lets it proper to receive sublimatic inks, without they enter into the fibers, guaranteing a good release during the transfer For digital transfer printing with water-based sublimating ink.

### **TECHNICAL SPECIFICATIONS**

WEIGHT 50 gsm/sqm
THICKNESS 69 my
ROLLS KENGHT 280 mt
AVAILABLE WIDTHS 162 cms
INNER ROLL DIAMETRE 3"

UTILISATION transfer on all polyestere fabrics, above all clothing and interiors ones

Very good if there are not high ink charges

Transfer with calander

- APPLICATION TEMPERATURE it changes according to the fabric and we suggest to test the paper

before using it.

Generally, the application temperature is 195-205°C for 45-60 seconds

- QUALITY good drying time

good definition of printing details

good colour releasing

no ghost effect after transfer very good dimensional stability

#### **STORAGE**

- Keep dry
- It's suggested the utilisation in environment with a moisture of 45% and 23°C
- It's suggested to leave the paper without packing before using it
- Duration: 2 years if stocked in proper conditions and in the original packing

## PARTICULAR EQUIPMENTS AVAILABLE ON REQUEST

#### VIRAX BORGHI ITALIA S.R.L.

Sede: Via Edison, 2 20090 Segrate (MI) - Tel. 02 26922041 - virax@virax.it

Filiale Veneto: Via dell'Artigianato, 13 31033 Castelfranco Veneto (TV) - Tel. 0423 720155

Filiale Centro Italia: Z.na Industriale Vallecupa 64010 Colonnella (TE) - Tel. 0861 749563

Filiale Toscana: Via Provinciale di Mercatale, 140 50059 Vinci (FI) - Tel. 335 6570468